

Appl. No. 09/902,277

CLAIMS

46
33. (Amended) A method of forming a bottom-gated thin film transistor comprising the following steps:

forming a transistor gate;

forming a polycrystalline thin film transistor layer over the transistor gate;

forming a fluorine-containing layer proximate the polycrystalline thin film transistor layer, the fluorine-containing layer comprising tungsten; and

transferring fluorine into the polycrystalline thin film transistor layer from the fluorine-containing layer.

47
34. The method of claim 33 wherein the polycrystalline thin film transistor layer comprises silicon.

48
35. (Amended) The method of claim 33 wherein the forming a fluorine-containing layer comprises chemical vapor deposition utilizing WF_6 and SiH_4 precursors.

49
36. (Amended) The method of claim 35 further comprising, after the transferring fluorine, removing the fluorine-containing layer from over the thin film transistor layer.

Appl. No. 09/902,277

50
37. (Amended) A method of forming a bottom-gated thin film transistor comprising the following steps:

forming a transistor gate;

forming a polycrystalline thin film transistor layer over the transistor gate;

forming a fluorine-containing layer over the transistor gate and over the polycrystalline thin film transistor layer;

providing a buffering layer intermediate the thin film transistor layer and the fluorine-containing layer; and

transferring fluorine into the polycrystalline thin film transistor layer over the transistor gate from the fluorine-containing layer.

51
38. (New) The method of claim 37 wherein the fluorine-containing layer comprises tungsten.

52
39. (New) The method of claim 37 wherein the buffering layer comprises SiO₂.

53
40. (New) The method of claim 37 wherein the polycrystalline thin film transistor layer comprises germanium.